

# TECHNICAL DATA SHEET

## IGL Coatings™ Ecocoat Premier



Material no. **154282** Revision date **30.05.2019**  
Version **1.14**

### IGL COATINGS ECOCOAT PREMIER

**A COATING SYSTEM FOR HYDRO AND OLEOPHOBIC TREATMENT OF PAINTS (ALKYD, ACRYLIC, POLYURETHANES, EPOXIES).**

#### DESCRIPTION

**ecocoat premier** is a user-friendly VOC-free coating system for almost all types of paints surfaces. **ecocoat premier** is water-based, long-term gloss retention, outstanding weathering resistance and excellent finish quality coating system. The consumption of the product will depend on the application method, approximately 5-10 ml/m<sup>2</sup> is sufficient for most applications.

#### Technical data

Property	Value	Method
Flash point	Would not flash	DIN 51755
Boiling point	Not applicable	DIN 51755
Specific Gravity	1 (at 20°C)	DIN 51757

#### Applications

Treatment of automotive, marine and aviation paints.

#### Processing

- Do not apply the product at temperatures below 5°C (41°F).
- Do not expose the surfaces to be treated to direct sunlight prior or during application.
- The surface must not be hot during application.
- Provide adequate ventilation and fresh air during application.
- If the substrate was previously treated with a coating system, proper removal, preferably with a polishing agent is important to ensure that the products bonds with the surface.

#### Step 1: Cleaning the surface

- The temperature during application should be in the range of 5-40°C (41-104°F), **preferably 20-26°C (68-78.8°F)**.
- In order to permit sufficient chemical bonding of **ecocoat premier** to the substrate, the surface must be carefully cleaned of all contaminants before the application. The long-term stability and abrasion resistance of the coating depends on how well **ecocoat premier** has chemically bonded with the surface.
- It is highly recommended to polish the surface with an abrasive system to remove all hard bearing contaminations on the surface.
- The additional use of **ecoclean iron** is recommended to remove iron particles or fallout.
- Use **ecoclean wash** to thoroughly remove all remaining residue and leftover film on the surface.
- Dry the surface before degreasing the surface with **ecoclean multi** or **ecoclean precoat**. It is recommended to use the IGL Microfiber Cloth for degreasing. The degreasing ensures a completely clean and reactive paint surface.
- Coat the cleaned surface immediately after cleaning to prevent any contamination.

#### Step 2: Treatment process

- Shake **ecocoat premier** before use.
- Spray some **ecocoat premier** onto a clean dry IGL Microfiber Cloth.
- Apply the product lightly on the surface in a 3x3 feet area, in a vertical (up and down) then horizontal (left and right) motion.
- Always ensure the areas coated are overlapping.
- Polish the coated surface in until the haze disappears.
- Allow the coating to cure for 30 minutes (5-50°C or 41-122°F), then apply a second layer and polish until the haze disappears.

# TECHNICAL DATA SHEET

## IGL Coatings™ Ecocoat Premier



Material no.	<b>154282</b>	Revision date	<b>30.05.2019</b>
Version	<b>1.14</b>		

- The hydrophobic effect generally can be seen depending on the substrate, reactivity and temperature after its initial curing stage and is further enhanced after a few minutes.
- Air dry the coated surface after application for approximately 4 hours and avoid contact with water.

### Curing Time

- The applied coating will be ready to be layered in 30 minutes (5-50°C or 41-122°F).

### Cleaning and Maintenance

Surfaces coated with **ecocoat premier** should be cleaned with cleaners in the pH range 3-9. Strong (mineral) acids or alkalis should be avoided and are also unnecessary as neutral cleaners are generally sufficient to clean vehicles coated with **ecocoat premier**.

### Safety and handling

For your safety, toxicological data and information on property transportation, storage and use, please read the Material Safety Data Sheet (MSDS) before using any **IGL Coatings products**. The MSDS is available upon request via email from [sales@iglcoatings.com](mailto:sales@iglcoatings.com).

### Disposal:

Disposal of this product, solutions and any byproducts should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements. Avoid dispersal of split material and runoff and contact with soil, waterways, drains and sewers.

### Storage

**ecocoat premier** is storage-stable for at least 12 months in originally sealed containers.

Opened bottles should be used within 6 months.

---

THIS INFORMATION AND ALL TECHNICAL AND OTHER ADVISE PROVIDED HEREIN ARE BASED ON IGL COATINGS'S PRESENT KNOWLEDGE AND EXPERIENCE. IGL COATINGS ASSUMES NO LIABILITY FOR SUCH INFORMATION OR ADVISE, INCLUDING THE EXTEND TO WHICH SUCH INFORMATION OR ADVISE MAY RELATE TO THIRD PARTY INTELLECTUAL PROPERTY RIGHTS. IGL COATINGS RESERVES THE RIGHT TO MAKE ANY CHANGES TO ANY INFORMATION OR ADVISE AT ANY TIME WHATSOEVER, WITHOUT ANY PRIOR OR SUBSEQUENT NOTICE TO ANY THIRD PARTY. IGL COATINGS DISCLAIM ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF IGL COATINGS IS AWARE OF SUCH PURPOSE), OR OTHERWISE. IT IS THE CUSTOMER'S SOLE RESPONSIBILITY TO ARRANGE FOR INSPECTION AND TESTING OF ALL PRODUCTS BY QUALIFIED EXPERTS. IGL COATINGS SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND ARISING FROM THIS ADVISE.